
OX-TRAN® Model 1/50

Oxygen Transmission Rate Test System





Features

Low cost – Uncompromised MOCON quality

Robust build provides dependability Designed for a lifetime of daily use

Easy to install - Simple to use

Effortless installation by user Practical built-in software minimizes user error Advisory screen prompts operator input Safety systems prevent sensor damage No flow adjustment required No calibration (absolute and coulometric) Customize and store 99 test methods 'Quick Start' function speeds set-up time System protects against over or under pressure System protects against thermo runaway

Easy to read screens (4" x 6") (10cm x 15cm)

Four status screens display real-time information Four intuitive configuration screens Step-by-step calibration screens Archivable, downloadable results

Horizontal test cell


Convenient film mounting Pneumatic clamp for consistent clamping force

Stand alone - Small footprint (11.5" x 15") (29cm x 38cm)

Takes up less space than many computers

Frequency Modulated

Faster & automatic Relative Humidity controls Generates the same RH on both sides of the film



Screen shot of easy to view Status screen shown 25% actual area size

Other screens include:
Zero Graph
TR Graph
Results
Tools
Settings
Methods
Calibrate



Technical Specifications

OX-TRAN® Model 1/50

Oxygen Transmission Rate	
OTR Range 50cm ²	0.1-200 cc/m² day
OTR Range 5cm ²	1.0-2000 cc/m² day
OTR Repeatability (50cm², 37.8° C)	± 0.05 cc/m² day absolute or ± 2% relative (whichever is greater)
Test Method	Coulometric (sensor in cell)
Film Area	50cm ²
RH (oxygen & carrier gas side)	Dry, 5 - 90% RH
RH Probe Accuracy	± 3%
Gas Requirement	99.9% Dry Nitrogen
Gas Pressure Range	30 - 35 psig
Temperature Range	10 - 40C
Memory	
Product Memory Capacity	99 methods
Result Storage	Current test and last result after test
Compliance	
CE/CSA/UL Listed	
Barometer	Automatic Pressure Correction 0-1000mmHg
Cell Clamping	Pneumatic

Visit Us On The Web: www.mocon.com



7500 Boone Ave. N Minneapolis, MN 55428 P: 763.493.6370 F: 763.493.6358

MOCON Commitment

The new system is another example of MOCON's 40 year commitment to innovation and quality in the design of permeation testing systems for barrier material assessment.

MOCON and OX-TRAN are registered trademarks, and PermNet and WinPerm are trademarks of MOCON. Copyright © 2008 MOCON, Inc.

MOCON reserves the right to change specifications without notice as part of our continuous program of product improvement.